

OFFICIAL

Attorney Docket No. P66680US0

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of: Michael KNEPPER et al.

Via facsimile

Application No.: 09/831,377

703-872-9310

Art Unit: 1742

Filed: August 22, 2001

Examiner: IP, Sikyin

For USE OF ZINC ALLOYS

TRANSMITTAL

Commissioner for Patents
 United States Patent and Trademark Office
 Washington, D.C. 20231

Sir:

Transmitted by facsimile herewith is Amendment, including inventorship declaration.

Fee Calculation						
	Nº of Claims		Excess Claims	Paid Excess Claims Of Record	Small Entity Fee	Large Entity Fee
Total		⊖ 20 =			⊗ \$9 = \$	⊗ \$18 = \$
Ind.		⊖ 3 =			⊗ \$42 = \$	⊗ \$84 = \$
() Multiple Dependent Fee (First Presentation)					⊗ \$140 = \$	⊗ \$280 = \$
Excess Claims Fee					\$	\$
Extension of Time Fee					\$	\$
Other:					\$	\$
Total Fee Due					\$	\$

☐ A check for \$ is attached.☐ Charge \$ to Deposit Account No. 06-1358.

☒ If a petition for extension of time is necessary but not enclosed, the Commissioner is petitioned to extend the time for response. The Commissioner is authorized to charge payment of any fees associated with this communication to Deposit Account No. 06-1358.

JACOBSON HOLMAN PLLC
 400 Seventh Street, N. W.
 Washington, D.C. 20004-2201
 Date: December 26, 2002
 WEP:jd
 R:\rbhomas\2002\DECEMBER\P66680US0-transmittal.wpd

By:

William E. Player

Registration No. 31,409

FAX RECEIVED
 DEC 27 2002
 GROUP 1700

Attorney Docket No. P66680US0

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of: Michael KNEPPER et al.

Via facsimile

Application No.: 09/831,377

703-872-9310

Art Unit: 1742

Filed: August 22, 2001

Examiner: IP, Sikyin

For USE OF ZINC ALLOYS

AMENDMENT

Commissioner for Patents
United States Patent and Trademark Office
Washington, D.C. 20231

Sir:

The instant paper transmitted by facsimile responds to the Office Action mailed September 26, 2002.

IN THE CLAIMS

Cancel claim 1 without prejudice or disclaimer and add the following claims.

2. A zinc alloy containing
- a) 8 to 15% by weight of aluminum
 - b) an alloy component selected from the group consisting of
 - 0.002 to 0.4% by weight of titanium,
 - 3 to 100 ppm of boron,
 - 3 to 50 ppm of magnesium, and
 - a combination thereof,
 - c) a second alloy component selected from the group consisting of

FAX RECEIVED
DEC 27 2002
GROUP 1700